



**CONCRETE-CURING
MEMBRANE**

SPECIFICATION FOR

CALCURE * CR

REQUIREMENT: Efficient concrete curing by a single spray application, without external covering or continuous water application.

PRODUCT TO USE: **CALCURE CR**

HOW TO SPECIFY: "All concrete shall be cured by a liberal application of Calcure CR sprayed on to the surface as soon as possible after finishing or removal of forms. 5-7 square meters per litre depending on efficiency required.

EFFECTS: Calcure CR is a special formulation incorporating chlorinated rubber which seals the surface of fresh concrete reducing moisture loss, giving high efficiency curing. Calcure CR complies with ASTM C309-66.

WHERE RECOMMENDED: All concrete surfaces which will be subject to traffic during the curing period, and areas to which standard curing methods would be difficult or uneconomical. After the curing period, preferably at the end of the job, an additional application of Calcure CR will seal the dry concrete against dusting and facilitate cleaning.
CONTACT CEMENTAID FOR APPLICATION SERVICE

CAUTION: Do not specify Calcure CR or other membrane curing compounds when surface hardeners such as CEMENTAID "DIAMITE" are specified to be used as penetration of these treatments would be impaired. In such cases, specify water, damp sand or building paper curing.

"Detailed information on special uses, test results, projects previously using products, and special recommendations are available from the CEMENTAID Technical Office."

For application Rega pneumatic knapsack spray is recommended with No. 9, 10 or 11 fantail nozzles. Equipment should be cleaned with solvent based thinners such as Xylol.

INDUSTRIAL FLOOR SPECIFICATIONS - GEL CONTROL AGENT - ANTI-CORROSION IMPREGNATIONS - OIL & SOLVENT PROOFING - WATERPROOFING - RAPID HARDENING RETARDING - SURFACE TOUGHENING - MORTAR AND DAMPCOURSE ADMIXTURES, ETC.

The information and recommendations herein are, as a result of experience and testing, accurate to the best of the seller's knowledge. However, as the proposed use and the circumstances surrounding such use are not known to the seller, it does not guarantee or warrant the product's suitability in any particular instance and shall not be liable for any loss or damage consequent upon any use whatsoever unless the seller has otherwise stipulated the product's suitability for a particular use in writing signed by a Director of the seller.

TECHNICAL SERVICE OFFICES				
VICTORIA	NEW SOUTH WALES	QUEENSLAND	WESTERN AUSTRALIA	SOUTH AUSTRALIA
Tel: (61) 3 9890 0487	Tel: (61) 2 9810 0725	Tel: (61) 7 3844 6992	Tel: (61) 8 9470 5858	Tel: (61) 8 8346 9711
Fax: (61) 3 9890 6223	Fax: (61) 2 9810 4164	Fax: (61) 7 3846 3825	Fax: (61) 8 9470 5999	Fax: (61) 8 8346 9977
CEMENTAID (VIC.) Pty. Ltd.	CEMENTAID (N.S.W.) Pty. Ltd.	CEMENTAID (QLD.) Pty. Ltd.	CEMENTAID (W.A.) Pty. Ltd.	CEMENTAID (S.A.) Pty. Ltd.
15 Clarice Road, Box Hill VIC 3128	44 Alberto Street, Lilyfield NSW 2040	242 Montague Road, West End QLD 4101	200 Star Street, Carlisle WA 6101	70 Cheif Street, Brompton SA 5007
INTERNET SITE www.cementaid.com.au				A.C.N. 000 376 625

*Regd. Trade Mark